










APOLLO COMFORT CONSTRUCTION SPECIFICATION

	<p>CONSTRUCTION</p> <table border="0"> <tr> <td>MACHINE GAUGE</td> <td></td> <td>1/8th Gauge</td> </tr> <tr> <td>PILE HEIGHT</td> <td>ISO 1766</td> <td>10.2 mm</td> </tr> <tr> <td>TUFT DENSITY</td> <td>ISO 1763</td> <td>136,399 tufts/m²</td> </tr> <tr> <td>PILE WEIGHT</td> <td></td> <td>1,424 gms/m² (42 oz/yd²)</td> </tr> <tr> <td>TOTAL CARPET WEIGHT</td> <td>ISO 8543</td> <td>2,361 gms/m²</td> </tr> <tr> <td>CARPET THICKNESS</td> <td>ISO 1765</td> <td>12.9 mm</td> </tr> <tr> <td>WIDTH</td> <td></td> <td>4 & 5 metre</td> </tr> </table>	MACHINE GAUGE		1/8th Gauge	PILE HEIGHT	ISO 1766	10.2 mm	TUFT DENSITY	ISO 1763	136,399 tufts/m ²	PILE WEIGHT		1,424 gms/m ² (42 oz/yd ²)	TOTAL CARPET WEIGHT	ISO 8543	2,361 gms/m ²	CARPET THICKNESS	ISO 1765	12.9 mm	WIDTH		4 & 5 metre
MACHINE GAUGE		1/8th Gauge																				
PILE HEIGHT	ISO 1766	10.2 mm																				
TUFT DENSITY	ISO 1763	136,399 tufts/m ²																				
PILE WEIGHT		1,424 gms/m ² (42 oz/yd ²)																				
TOTAL CARPET WEIGHT	ISO 8543	2,361 gms/m ²																				
CARPET THICKNESS	ISO 1765	12.9 mm																				
WIDTH		4 & 5 metre																				
	<p>COMPOSITION</p> <table border="0"> <tr> <td>PILE CONTENT</td> <td>ISO 1833</td> <td>100% Soft Excellon Polypropylene</td> </tr> <tr> <td>PRIMARY BACKING</td> <td></td> <td>Woven Polypropylene</td> </tr> <tr> <td>SECONDARY BACKING</td> <td></td> <td>Woven Secondary</td> </tr> </table>	PILE CONTENT	ISO 1833	100% Soft Excellon Polypropylene	PRIMARY BACKING		Woven Polypropylene	SECONDARY BACKING		Woven Secondary												
PILE CONTENT	ISO 1833	100% Soft Excellon Polypropylene																				
PRIMARY BACKING		Woven Polypropylene																				
SECONDARY BACKING		Woven Secondary																				
	<p>PERFORMANCE</p> <table border="0"> <tr> <td>SUITABILITY</td> <td></td> <td>Heavy Domestic</td> </tr> <tr> <td>WIRA ABRASION TEST</td> <td>PD 6527:Clause 17</td> <td>Exceeds 25,000 Rubs</td> </tr> <tr> <td>STATIC LOADING</td> <td>ISO 3416</td> <td>24.2% Thickness loss after 24 hrs recovery</td> </tr> <tr> <td>DYNAMIC LOADING</td> <td>ISO 2094</td> <td>44.1% Thickness loss after 1,000 impacts</td> </tr> <tr> <td>TUFT ANCHORAGE</td> <td>ISO 4919</td> <td>Above 1 kg</td> </tr> </table>	SUITABILITY		Heavy Domestic	WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 25,000 Rubs	STATIC LOADING	ISO 3416	24.2% Thickness loss after 24 hrs recovery	DYNAMIC LOADING	ISO 2094	44.1% Thickness loss after 1,000 impacts	TUFT ANCHORAGE	ISO 4919	Above 1 kg						
SUITABILITY		Heavy Domestic																				
WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 25,000 Rubs																				
STATIC LOADING	ISO 3416	24.2% Thickness loss after 24 hrs recovery																				
DYNAMIC LOADING	ISO 2094	44.1% Thickness loss after 1,000 impacts																				
TUFT ANCHORAGE	ISO 4919	Above 1 kg																				
	<p>COLOUR FASTNESS</p> <table border="0"> <tr> <td>LIGHT FASTNESS</td> <td>ISO 105-B02</td> <td>6 on all colours</td> </tr> <tr> <td>WET FASTNESS</td> <td>ISO 105-E01</td> <td>4/5 on all colours</td> </tr> <tr> <td>SHAMPOO FASTNESS</td> <td>BS 1006:UK-TB</td> <td>5 on all colours</td> </tr> </table>	LIGHT FASTNESS	ISO 105-B02	6 on all colours	WET FASTNESS	ISO 105-E01	4/5 on all colours	SHAMPOO FASTNESS	BS 1006:UK-TB	5 on all colours												
LIGHT FASTNESS	ISO 105-B02	6 on all colours																				
WET FASTNESS	ISO 105-E01	4/5 on all colours																				
SHAMPOO FASTNESS	BS 1006:UK-TB	5 on all colours																				
	<p>THERMAL VALUE</p> <table border="0"> <tr> <td>TOG VALUE</td> <td>ISO 5085-1</td> <td>1.8 Tog</td> </tr> <tr> <td>THERMAL RESISTANCE</td> <td></td> <td>0.18 m² k/w</td> </tr> </table>	TOG VALUE	ISO 5085-1	1.8 Tog	THERMAL RESISTANCE		0.18 m ² k/w															
TOG VALUE	ISO 5085-1	1.8 Tog																				
THERMAL RESISTANCE		0.18 m ² k/w																				
	<p>FLAMMABILITY</p> <table border="0"> <tr> <td>CE MARK RATING</td> <td></td> <td>Efl</td> </tr> <tr> <td>METHENAMINE PILL TEST</td> <td>BS 4790</td> <td>Pass - Low radius of ignition</td> </tr> </table>	CE MARK RATING		Efl	METHENAMINE PILL TEST	BS 4790	Pass - Low radius of ignition															
CE MARK RATING		Efl																				
METHENAMINE PILL TEST	BS 4790	Pass - Low radius of ignition																				
	<p>CHEMICAL IMPACT</p> <table border="0"> <tr> <td>FORMALDEHYDE</td> <td>CE</td> <td>E1</td> </tr> </table>	FORMALDEHYDE	CE	E1																		
FORMALDEHYDE	CE	E1																				
	<p>BIOLOGICAL ATTACK</p> <table border="0"> <tr> <td>MOTH / INSECT RESISTANT</td> <td></td> <td>Insect & rot proof</td> </tr> </table>	MOTH / INSECT RESISTANT		Insect & rot proof																		
MOTH / INSECT RESISTANT		Insect & rot proof																				
	<p>ANTI STATIC</p> <table border="0"> <tr> <td></td> <td></td> <td>-0.0 kv (Requirement less than +2.0 kv)</td> </tr> </table>			-0.0 kv (Requirement less than +2.0 kv)																		
		-0.0 kv (Requirement less than +2.0 kv)																				

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.

April 2018



GREENWOOD & COOPE LTD. Brookhouse Mill, Greenmount, Bury, Lancashire BL8 4HR
 TEL: 01204 881234 FAX: 01204 887722
 E-MAIL: info@cormarcarpets.co.uk WEBSITE: www.cormarcarpets.co.uk

