TECHNICAL SPECIFICATION

A Comment	

CONSTRUCTION ELITE **DELUXE** MACHINE GAUGE 1/8th Gauge Cut Pile Twist 1/8th Gauge Cut Pile Twist PILE HEIGHT ISO 1766 7.5 mm

TUFT DENSITY ISO 1763 120,899 tufts/m² 130,199 tufts/m²

PILE WEIGHT 1,525 gms/m² 1,864 gms/m² 45 oz/yd² 55 oz/yd² TOTAL CARPET WEIGHT ISO 8543 2,462 gms/m² 2,801 gms/m² CARPET THICKNESS ISO 1765 10.5 mm 12 mm WIDTH 4 & 5 metre 4 & 5 metre



COMPOSITION

PILE CONTENT PRIMARY BACKING SECONDARY BACKING

Woven Polypropylene Woven Secondary

80% Wool, 10% Nylon, 10% Tuftbond Polyester 80% Wool, 10% Nylon, 10% Tuftbond Polyester

Woven Polypropylene Woven Secondary



MC

PERFORMANCE

SUITABILITY WIRA ABRASION TEST STATIC LOADING DYNAMIC LOADING TUFT ANCHORAGE

PD 6527: Clause 17 ISO 3416 ISO 2094

ISO 4919

ISO 1833

Extra Heavy Domestic Exceeds 24.000 Rubs

27.1% Thickness Loss after 24 hrs recovery 29.2% Thickness Loss after 1,000 impacts

Above 1.2 kg

Extra Heavy Domestic / Medium Contract Exceeds 24.000 Rubs

22.9% Thickness loss after 24 hrs recovery 22.1% Thickness loss after 1,000 impacts

Above 1.2 kg



COLOUR FASTNESS

LIGHT FASTNESS 5/6 on all colours 5/6 on all colours ISO 105-B02 WET FASTNESS ISO 105-E01 4/5 on all colours 4/5 on all colours SHAMPOO FASTNESS BS 1006: UK-TB 4/5 on all colours 4/5 on all colours



THERMAL VALUE

TOG VALUE ISO 5085-1 1.3 Tog 1.3 Tog THERMAL RESISTANCE $0.13 \, \text{m}^2 \, \text{k/w}$ $0.13 \, \text{m}^2 \, \text{k/w}$

FLAMMABILITY

CE MARK RATING HOT METAL NUT TEST METHENAMINE PILL TEST

BS4790

ISO 6925

CE Dfl. S1

Pass - Low radius of ignition

Dfl. S1

Pass - Low radius of ignition



CHEMICAL IMPACT

FORMALDEHYDE

CE E1

Εī



BIOLOGICAL ATTACK

MOTH / INSECT RESISTANT **Eulan Treated** Eulan Treated



ANTI STATIC

-0.1 kv (Requirement less than +2.0kv)

-0.1 kv (Requirement less than +2.0kv)

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.